



Mobilgrease XHP™ 220 Series

Mobil Grease , United States

Product Description

Mobilgrease XHP™ 220 greases are extended service lithium complex greases intended for a wide variety of applications and severe operating conditions. These greases were designed to outperform conventional products by applying cutting edge, proprietary, lithium complex manufacturing technology. They are formulated to provide excellent high temperature performance with superb adhesion, structural stability and resistance to water contamination. These greases have a high level of chemical stability and offer excellent protection against rust and corrosion. These greases feature high dropping points and maximum recommended operating temperature of 140° C (284°F). Mobilgrease XHP 220 greases are available in NLGI grades 00, 0, 1, 2 and 3 with an ISO VG 220 base oil viscosity.

Mobilgrease XHP 220 greases are designed for a wide range of applications including the industrial, automotive, construction and marine sectors. Their performance features make them ideal choices for operating conditions including high temperature, water contamination, shock loading and extended re-lubrication operations. Mobilgrease XHP 222 Special is an extreme pressure grease fortified with 0.75% molybdenum disulfide that provides protection from wear under conditions pivoting and other conditions that lead to loss of oil film.

Features and Benefits

Mobilgrease XHP 220 greases are leading members of the Mobilgrease brand of products, which have gained a reputation for innovation and performance excellence. Mobilgrease XHP 220 greases are high performance products designed by our formulation technologists and backed by our world-wide technical support staff.

A key factor in the excellent adhesion and cohesion properties and high drop point of Mobilgrease XHP 220 greases is the proprietary manufacturing technology developed at our research facilities and adopted by our modern manufacturing facilities. These products use specially selected additives to provide excellent oxidation stability, rust and corrosion control, resistance to water contamination as well as anti-wear and EP protection. Mobilgrease XHP 220 Series products offer the following features and potential benefits:

Features	Advantages and Potential Benefits
Superb resistance to water washout and spray-off	Helps assure proper lubrication and protection even in the most severe water exposure conditions
Highly adhesive and cohesive structure	Excellent grease tenacity, helps reduce leakage and extend re-lubrication intervals for reduced maintenance requirements
Excellent rust and corrosion resistance	Protection of lubricated parts even in hostile aqueous environments
Very good resistance to thermal, oxidative and structural degradation at high temperature	Helps extend grease life and enhance bearing protection in high temperature applications helping to reduce maintenance and replacement costs
Very good anti-wear and EP performance	Reliable protection of lubricated equipment, even under conditions of high sliding with potential for extended equipment life and reduced unanticipated downtime
Broad multi-purpose application	Provides potential for inventory rationalization and reduced inventory costs

Applications

Mobilgrease XHP 220 greases are used in a wide range of equipment including industrial, automotive, construction and marine applications. Their blue color enables easy verification of application:

Mobilgrease XHP 005 and 220 are softer, high-temperature greases recommended by ExxonMobil for centralized grease application systems, gear lubrication, and where extreme-cold-temperature pumpability is important.

Mobilgrease XHP 221 is recommended by ExxonMobil for use in industrial and marine applications, chassis components and farm equipment. It provides excellent low temperature performance.

Mobilgrease XHP 222 is recommended by ExxonMobil for industrial and marine applications, chassis components and farm equipment. Its sticky formulation stays in applications longer.

Mobilgrease XHP 223 is recommended by ExxonMobil for applications where good high temperature and anti-leakage properties are required. It is particularly recommended for severe truck wheel bearing applications or for rolling element bearings subject to vibration, or where higher speeds require a grease with higher consistency to provide channeling characteristics.

Mobilgrease XHP 222 Special contains 0.75% molybdenum disulfide, is grey in color and is recommended by ExxonMobil for moderate duty service in industrial applications, chassis components and farm equipment. It also finds application in king pins, U-joints, fifth wheels and bucket pins.

Specifications and Approvals

This product has the following builder approvals:	220	221	222
Fives Cincinnati P-64			X
Fives Cincinnati P-72		X	
Fives Cincinnati P-79	X		

This product meets or exceeds the requirements of:	220	221	222
DIN 51825:2004-06 - KP 1 N -20		X	
DIN 51825:2004-06 - KP 2 N -20			X

Properties and Specifications

Property	005	220	221	222	222 SPECIAL	223
Grade	NLGI 00	NLGI 0	NLGI 1	NLGI 2	NLGI 2	NLGI 3
Thickener Type	Lithium Complex	Lithium Complex	Lithium Complex	Lithium Complex	Lithium Complex	Lithium Complex
Base Oil Viscosity of Greases @ 40 C, mm ² /s, AMS 1697	220	220	220	220	220	220
Bomb Oxidation, Pressure Drop, 100 h, kPa, ASTM D942	35	35	35	35	35	35
Color, Visual	Dark blue	Dark blue	Dark blue	Dark blue	Grey-black	Dark blue
Copper Strip Corrosion, Rating, ASTM D4048	1B	1B	1B	1B	1B	1B

Property	005	220	221	222	222 SPECIAL	223
Corrosion Preventive Properties, Rating, ASTM D1743	PASS	PASS	PASS	PASS	PASS	PASS
Dropping Point, °C, ASTM D2265		270	280	280	280	280
Four-Ball Extreme Pressure Test, Weld Load, kgf, ASTM D2596	315	315	315	315	400	315
Four-Ball Wear Test, Scar Diameter, mm, ASTM D2266	0.5	0.5	0.5	0.5	0.5	0.5
Molybdenum Disulfide Content, wt %, CALCULATED					0.75	
Penetration, 60X, 0.1 mm, ASTM D217	415	370	325	280	280	235
Roll Stability, Penetration Consistency Change, 0.1 mm, ASTM D1831		-15	-15	0	0	0
SKF Emcor Rust Test, Distilled Water, ASTM D6138	0,0	0,0	0,0	0,0	0,0	0,0
Timken OK Load, kg, ASTM D2509	40	40	40	40	40	40

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

07-2020

Exxon Mobil Corporation

22777 Springwoods Village Parkway
Spring TX 77389

1-800-ASK MOBIL (275-6624)

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Energy lives here™

ExxonMobil



© Copyright 2003-2019 Exxon Mobil Corporation. All Rights Reserved